



TECHNICAL DATA

Single Component Clear

SNAP! Dry Erase Paint

One Quart covers 200 square feet

TEST	ASTM METHOD	RESULT
VOC	D3960	4 g/l
Density	D1475	9.44 lbs / Gal
Sag Resistance Crack Resistance/	D4400	<3mils
Elongation	D522	> 32%
Gloss 60 degree	D523	85–90@ 3 mil coating
QUV/500 Hrs, UVA 340	D4587	Visual Gloss Change - Minimal Visual Color Change – NONE Other Detrimental Film Effects-NONE DE = 1.40
Flammability	E-84	Flame Spread – 5 Smoke Development – 0
Flashpoint	D92	>200F
Scrub Resistance	D2486	> 15,000 Cycles
Washability	D3450	98.8%